












TECHNICAL SPECIFICATIONS

Technical specifications





Marmoleum meets the requirements of EN ISO 24011

		Marmoleum real FR	Marmoleum striato FR
 Total thickness	EN-ISO 24346	2.5 mm	2.5 mm
 Roll width	EN-ISO 24341	200 cm	200 cm
 Roll length	EN-ISO 24341	≤ 32 m	≤ 32 m
Minimum order quantity		3000 m ²	3000 m ²
 Total weight	EN-ISO 23997	2900 gram/m ²	2900 gram/m ²
 Residual indentation	EN-ISO 24343-1	≤ 0.15 mm	≤ 0.15 mm
 Light fastness	EN-ISO 105/B02	≥ 6	≥ 6
 Flexibility	EN-ISO 24344	Ø 40 mm	Ø 40 mm
 Resistance to chemicals	EN-ISO 26987	Resistant to diluted acids, oils, fats and to the conventional solvents. Not resistant to prolonged exposure to alkalis.	Resistant to diluted acids, oils, fats and to the conventional solvents. Not resistant to prolonged exposure to alkalis.
 Electrical resistance	EN 1081	1-10 ⁶ <R1<1-10 ⁸ Ω	1-10 ⁶ <R1<1-10 ⁸ Ω
 Contact sound insulation	ISO 717-2	Δ Lw = ≥ 5 dB	Δ Lw = ≥ 5 dB
 Tested flammability standards	EN 45545-2	HL2	HL3
	BS6853	1a	
	DIN 5510-2	SF 1-3	SF 1-3
	ASTM E.648 ASTM E.662	Class 1 pass	

Marmoleum meets the requirements of EN 14041



EN 14041

 Fire behaviour	EN 13501-1	B _{FL} -s1	B _{FL} -s1
 Slip resistance	EN 13893	DS: ≥ 0.30	DS: ≥ 0.30
 Body voltage	EN 1815	< 2 kV	< 2 kV
 Thermal conductivity	EN 12524	0.17 W/m·K	0.17 W/m·K

Marmoleum FR is made to order

Recolour
certain designs with



Marmoleum

marmoleum[®] FR

If you cannot see the exact colourway that you are looking for, please speak to us and we will work closely with you in order to match your specific requirements.